

Slot wedge NMNM 4-ply laminate, Nomex / Mylar / Nomex / Mylar with high dielectric strength and good mechanical and thermal properties. The prestressed profile warrants very high rigidity and stability and contributes to a fast, safe installation. Working temperature +155°C.



Typical applications

Suitable for winding applications.

Properties

- Good mechanical properties
- Adapted for class F varnishes
- Good electrical properties

Composition

- 4-ply laminate, Nomex/Mylar/Nomex/Mylar (calendered Nomex 50 µm)

Colour


- White

Packaging

- Bundles of 100 metres
- Length 1 000 mm

Technical data

- Temperature class F, 155°C
- Dielectric strength: -0.46 mm \geq 24 kV
- Thickness: 0.46 mm
- Thickness tolerance: \pm 15%



Item number	Type	Dimensions (mm)	Packaging	Dielectric strength (KV)	Tensile strength (N/mm ²)	Weight (g/m ²)	Thickness film (μm)
125395	NMNM 10 x 2	10 x 2 x 0.46 x 1000	100 m	≥ 24	≥ 300	460	250/23
125396	NMNM 12 x 3	12 x 3 x 0.46 x 1000	100 m	≥ 24	≥ 300	460	250/23
125397	NMNM 14 x 4	14 x 4 x 0.46 x 1000	100 m	≥ 24	≥ 300	460	250/23
125398	NMNM 16 x 5	16 x 5 x 0.46 x 1000	100 m	≥ 24	≥ 300	460	250/23
125399	NMNM 18 x 6	18 x 6 x 0.46 x 1000	100 m	≥ 24	≥ 300	460	250/23
125400	NMNM 20 x 7	20 x 7 x 0.46 x 1000	100 m	≥ 24	≥ 300	460	250/23
125401	NMNM 22 x 8	22 x 8 x 0.46 x 1000	100 m	≥ 24	≥ 300	460	250/23
125402	NMNM 24 x 9	24 x 9 x 0.46 x 1000	100 m	≥ 24	≥ 300	460	250/23
125403	NMNM 26 x 10	26 x 10 x 0.46 x 1000	100 m	≥ 24	≥ 300	460	250/23
125404	NMNM 28 x 12	28 x 12 x 0.46 x 1000	100 m	≥ 24	≥ 300	460	250/23

How to contact BEVI

Contact details for all countries are continually updated on our website.
Please visit www.bevi.com to access the information direct.

BEVI AB (Headquarters)
Blomstermåla, Sweden
Tel. +46 499 271 00
info@bevi.se